


TEST REPORT



No: 200127083

VERIFICATION WEBSITE: www.gttc.net.cn

VERIFICATION CODE: QIWD-2850-04

ISSUE DATE: 2020-05-23

扫码下载报告

APPLICANT:
ADDRESS:

[REDACTED]
[REDACTED]
[REDACTED], P. R. CHINA.

INFORMATION CONFIRMED BY APPLICANT:

MEDICAL PROTECTIVE CLOTHING

QUANTITY: 1 PIECE

BRAND: 3R MED

STYLE NO.: SR20200501001

COLOUR: BLUE

SIZE: SRIC-F-XXL

DATE RECEIVED/DATE TEST STARTED: 2020-05-19

CONCLUSION:

pH VALUE	M
FORMALDEHYDE CONTENT	M
DETERMINATION OF ODOURS	M
COLOUR FASTNESS TO PERSPIRATION	M
COLOUR FASTNESS TO WATER	M
COLOUR FASTNESS TO DRY RUBBING	M
BANNED AZO COLOURANTS	M

NOTE: "M" - MEET THE STANDARD'S REQUIREMENT "F" - FAIL TO MEET THE STANDARD'S REQUIREMENT
"___" - NO COMMENT

REMARK:

TESTED AND JUDGED BY GB 18401-2010 AS PER CLIENT'S REQUIREMENT.

THIS REPORT IS THE ENGLISH TRANSLATION VERSION OF THE REPORT 200127082.

ALL THE TESTED ITEMS ARE TESTED UNDER THE STANDARD CONDITION (EXCEPT FOR INDICATION).

COPIES OF THE REPORT ARE VALID ONLY RE-STAMPED.

THE EXPERIMENT WAS CARRIED OUT AT No. 1, ZHUJIANG ROAD, PANYU DISTRICT, GUANGZHOU, GUANGDONG, P. R. CHINA.



APPROVED BY:

Nan Ma ENGINEER

马楠

PAGE 1 OF 4

TEST REPORT

No: [REDACTED]



PAGE 2 OF 4

TEST REPORT

No: [REDACTED]

pH VALUE

(GB/T 7573-2009, 0.1mol/L KCl EXTRACTING SOLUTION)
(GB/T 7573-2009 MOD ISO 3071:2005)

6.4

REQUIREMENT
4.0~8.5 CLASS B
(GB 18401-2010)

FORMALDEHYDE CONTENT

(GB/T 2912.1-2009, WATER EXTRACTION METHOD)
(GB/T 2912.1-2009 MOD ISO 14184-1:1998)

NOT DETECTED

REQUIREMENT
≤75 mg/kg CLASS B
(GB 18401-2010)

REMARK: DETECTION LIMIT 20mg/kg

DETERMINATION OF ODOURS

(GB 18401-2010 6.7)

NO ABNORMAL ODOUR

REQUIREMENT
NO ABNORMAL ODOUR
(GB 18401-2010)

COLOUR FASTNESS TO PERSPIRATION (GRADE)

(GB/T 3922-2013)
(GB/T 3922-2013 MOD ISO 105-E04:2013)

	ACID	ALKALINE	REQUIREMENT
COLOUR CHANGE	4	4	≥3
COLOUR STAINING			≥3
- ACETATE	4-5	4-5	(GB 18401-2010)
- COTTON	4-5	4-5	
- POLYAMIDE	4-5	4-5	
- POLYESTER	4-5	4-5	
- ACRYLIC	4-5	4-5	
- WOOL	4-5	4-5	

COLOUR FASTNESS TO WATER (GRADE)

(GB/T 5713-2013)
(GB/T 5713-2013 MOD ISO 105-E01:2013)

COLOUR CHANGE	4	REQUIREMENT
COLOUR STAINING		≥3
- ACETATE	4-5	≥3
- COTTON	4-5	(GB 18401-2010)
- POLYAMIDE	4-5	
- POLYESTER	4-5	
- ACRYLIC	4-5	
- WOOL	4-5	

COLOUR FASTNESS TO DRY RUBBING (GRADE)

(GB/T 3920-2008)
(GB/T 3920-2008 MOD ISO 105-X12:2001)

LENGTH	4-5	WIDTH	4-5	REQUIREMENT
				≥3
				(GB 18401-2010)



PAGE 3 OF 4

TEST REPORT

No: [REDACTED]

PAKED AZO COLOURANTS

TEST METHOD: GB/T 17592-2011, GENERAL PRETREATMENT

FORBIDDEN AMINE

	CAS NO.	REQUIREMENT (mg/kg)	RESULT (mg/kg)
4-aminobiphenyl	[92-67-1]	≤20	N
benzidine	[92-87-5]	≤20	N
4-chloro-o-toluidine	[95-69-2]	≤20	N
2-naphthylamine	[91-59-8]	≤20	N
o-aminoazotoluene	[97-56-3]	≤20	N
5-nitro-o-toluidine	[99-55-8]	≤20	N
p-chloroaniline	[106-47-8]	≤20	N
2,4-diaminoanisole	[615-05-4]	≤20	N
4,4'-diaminobiphenylmethane	[101-77-9]	≤20	N
3,3'-dichlorobenzidine	[91-94-1]	≤20	N
3,3'-dimethoxybenzidine	[119-90-4]	≤20	N
3,3'-dimethylbenzidine	[119-93-7]	≤20	N
3,3'-dimethyl-4,4'-diaminobiphenylmethane	[838-88-0]	≤20	N
p-cresidine	[120-71-8]	≤20	N
4,4'-methylene-bis-(2-chloroaniline)	[101-14-4]	≤20	N
4,4'-oxydianiline	[101-80-4]	≤20	N
4,4'-thiodianiline	[139-65-1]	≤20	N
o-toluidine	[95-53-4]	≤20	N
2,4-toluyldiamine	[95-80-7]	≤20	N
2,4,5-trimethylaniline	[137-17-7]	≤20	N
o-anisidine	[90-04-0]	≤20	N
2,4-xylydine	[95-68-1]	≤20	N
2,6-xylydine	[87-62-7]	≤20	N
4-aminoazobenzene	[60-09-3]	≤20	N

N MEANS LESS THAN THE DETECTION LIMIT OF 5mg/kg

RATING ACCORDING TO GB 18401-2010.

OVERALL RATING PASS



PAGE 4 OF 4

End of Report